

AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1. (Not entered): A manufacturing method of a polarizing film comprising steps of:  
contacting a protective film (B) comprising at least two layers having different softening points onto at least one face of a polarizer (A) comprising a stretched polymer film made of dyed hydrophilic polymer film, without using an adhesive, and  
thermocompression bonding.
2. (Original): The manufacturing method of the polarizing film according to Claim 1, wherein a heating treatment is performed from a side of the protective film (B).
3. (Original): The manufacturing method of the polarizing film according to Claim 1, wherein a heating treatment period of time is not more than five seconds.
4. (Original): The manufacturing method of the polarizing film according to Claim 1, wherein a heating treatment temperature is not less than 90°C.
5. (Original): The manufacturing method of the polarizing film according to Claim 1, wherein a pressurization is performed by applying a linear loads pressure at not less than 5 N/cm.
6. (Original): The manufacturing method of the polarizing film according to Claim 1, wherein thermocompression bonding is performed by applying a heating treatment and a pressurization simultaneously.
- 7-9. (Canceled)
10. (Previously presented): The manufacturing method of the polarizing film according to

claim 5, wherein the pressurization is performed at not less than 20 N/cm.

11. (Canceled)

12. (Not entered): The manufacturing method according to claim 1, wherein a softening point of a layer having a low softening point is not less than 80°C.

13. (Not entered): The manufacturing method according to claim 1, wherein a softening point of a layer having a low softening point is not less than 90°C.

14. (Not entered): The manufacturing method according to claim 1, wherein a difference between softening points of the layers is not less than 5°C.

15. (Not entered): The manufacturing method according to claim 1, wherein a difference between softening points of the layers is not less than 10°C.

16-18. (Canceled)